



b. Preceding Coat	2 coats Supro Putty 1 coat KORESEALER MULTI
c. Application Conditions	The surface must be completely clean and dry. Do not apply when relative humidity is above 85%. The surface temperatures must be at least 10°C above dew point to prevent condensation.
d. Thinning	Clean water. (Thinning ratio: Max.20%).
e. Method of Application	Brush, Roller or Spray application.
f. Film Thickness	Recommended per coat 30-40 microns dry film. Apply 2 times with proper film thickness
g. Recoating Interval	At 25°C/ 77°F, Minimum: 2 hours
h. Packing Unit	5L, 18L

#### 4. REMARKS

- a. Because of cracking problem, can not be used in the temperature below 5°C/41°F. Avoid excessive thinning. May be color difference and poor appearance, functionality deterioration.
- b. Protect to frost during transport or storage.
- c. When applying on old film or on surface applied with putty, check adhesion test prior to application.
- d. Must use sealer on irregular surface as a primer to avoid color difference according to the absorbed difference.
- e. Keep containers closed when not in use. Store out of children's reach.
- f. If you have any questions about products or you want to know safety information, you can get the technical datasheets and MSDS on our Internet Homepage ([www.kccvn.com.vn](http://www.kccvn.com.vn)) or ask the customer's service.