

\* Koreseal ZY0894 is a one component, low viscosity, moisture curing sealant based on Polyurethane, which cures by reaction with moisture to a elastic product. The skin formation and curing times are dependent on humidity and temperature. By increasing the temperature and moisture these times can be reduced.

Recommended \* Automotive Windshield / Backlite Glass Adhesion

use

- \* For panorama sunroof Front / Rear glass and module bonding
- \* Others (Guaranteed by KCC technical team)

## **Physical Properties**

Key

\* Easy application - can be cured by moisture in the air

- Performance \* Excellent adhesion on glass, ceramic coated glass(with Glass Primer ZY0893) and on painted or frame surfaces with Metal primer(ZY0892)
  - \* Excellent durability
  - \* Outstanding resistance to water, chemicals, weathering, ozone and ultraviolet
  - \* Excellent elongation (Above 300%)

Physical

\* Binder : Polyurethane resin

**Properties** 

\* Curing method : One-componet moisture cure

: Paste with high viscosity and black color \* Appearance

\* Specific Gravity : 1.22 - 1.42 \* Non-volatile : Above 95%

\* Skin formation time : Within 60min(20℃, 65% RH)

\* Pot life : Within 5min \* Hardness (Shore A) : 35 ~ 60HS \* Shear strength : >3.0MPa \* Elongation : > 300 %

### Application details

- Using Method | \* Before using the product, please keep the room temperature. (When stored where the temperature is sharply lower, discharge may occur issue)
  - \* Remove any dust, oil and grease, finger print and other contaminants from the surfaces (glass and painted steel panel)to be applied by gauze soaked with lead free gasoline or isopropyl alcohol.
  - \* Apply a suitable primer on the surfaces (Glass: G-PRIMER ZY0893, Painted steel panel and frame: M-PRIMER ZY0892) and allow to dry for approximately 1minutes.
  - \* Applying Koreseal ZY0894 on the glass coated with G-PRIMER ZY0893. Fix the glass to the car body(Painted steel panel) within 5minutes(on the basis of 20℃/68°F and R.H 65%) after applying Koreseal ZY0894.
  - ★ About 8 hours to cure, so early (20 °C, relative humidity 65% basis) this takes careful not subjected to external forces on the glass until the initial curing is achieved.
  - \*Final curing time after applying ZY0894 will take five days (20 °C, relative humidity 65% basis). And final properties and implementation will take seven days (20 °C, relative humidity of 65% basis).

# Cleaning

\* When necessary washing, it may be used an alcohol solvent until the chemical reaction with the

generation and within 1 min.

Note 1'st issue

Revision

2017-01-23

\* When washing your hands may be wiped by rubbing using a scrubbing brush and warm water or soapy water to 1 min.

Storage and	l package
Shelf life	* If stored according to manufacturer's instructions, the shelf life of the product four months.
Storage	* Koreseal ZY0894 is because the moisture-sensitive products are packed in drums stacked on the
	aluminum pack in a vacuum. The so after opening with air curing progress and ever have been opened
	products all use as possible, once opened the product is available by immersing the deprecation upon
	ejection nozzles for curing prevention(Process Oil). Do not let moisture in the air not penetrate.
Packing Unit	* ZY0894 is supplied to 240Kg/drum, 310ml / cartridge container.
Remarks	
Handling	* Because the moisture-curing before use in dry, indoor storage(5~35℃), and use within SHELF LIFE
Precautions	period.
	* Proper temperature range of applicator, PLATE each and plumbing equipment recommended by us wi

tell you that in 20 $\sim$ 25 $^{\circ}\mathrm{C}$ . Also, ensure application equipment is installed indoors.
* When applying equipment installed outdoors or where the temperature difference is severe, install the
ROOM temperature is maintained.
* When re-setting the temperature of the coating equipment (PLATE and the pipes) depending on the
surrounding environment during winter / summer and consultation with our technical team
* Long-term and DRUM PLATE discharge period is closed when you are using Let sealed with Alumina
Laminate or thick plastic.
* Since every drum replacement PLATE / exposed to the outside air, be sure to clean the debris DGU.
PLATE inside / outside of the by the cured product may be the cause of poor attachment and ejection
problems.
* Please refer to 'DGU Management Plan' for details of product usage and precautions.

Disclaimer: The information in this data sheet is believed to the best of our knowledge based on laboratory test and practical experience. However, there are many factors affecting the performance of product and the product quality itself, so we are not able to guarantee without the confirmation of the purpose of using the product from us in writing. We reserve the right to change the data without notice and you should check that this data sheet is current prior to using the product.

