



Product description	SL9100 is a two-component liquid silicone rubber for fabric label(Mixing ratio -A : B = 10 : 1)
Applications	Fabric Label and Anti-slip agent4.
Key performance properties	Good workability No by-products because of addition curing LSR Excellent transparency after curing and easy pigmentation

Typical Property Data

Benefits	-Low viscosity -Excellent fluidity -Rapid curing rate					
Typical properties	Property		Test method	Unit	Press 1stcure ²⁾	
	Before curing	Appearance	PTA	ASTM E 1767	-	Translucent
			PTB			Transparent
		Viscosity ¹⁾	PTA	ASTM D 4287	Pa.s	60
			PTB			5
		Mixing ratio (by weight)				10:1
	General properties	Pot life (23°C, Day)				1
		Appearance		ASTM E 1767	-	Translucent
		Specific gravity (at 23°C)		ASTM D 792	-	1.07
		Hardness		ASTM D 2240	Shore A	36
		Tensile Strength		DIN 53504	MPa	4.6
		Elongation		DIN 53504	%	450
		Tear Strength		ASTM D 624	N/mm	20
	1) Brookfield Viscometer HADV Type, Spindle No.6, 20 rpm 2) Brookfield Viscometer HADV Type, Spindle No.5, 20 rpm 3) Sheet curing conditions : press cure at 170°C/10 min Caution) Typical property data values should not be used as specifications					

Composition	-Silicone polymer -Silica
How to use	For making a suitable product, Mix components A and B in the ratio 10 : 1
Features	-High temperature vulcanizing and addition curing LSR

Storage and packaging

Shelf life and storage	Use it within 12 months from the day of manufacture. Store in a cool dry place out of direct sunlight. Keep out of the reach of the children.
Packaging	PART A : 20 kg PE Pail PART B : 1 kg Tin Can

Remarks

Handling	Wear eye protection and protective glove when handling this product.
Precautions	May cause a curing difficulty with amine, sulfur, organicphosphate compound, and organicmetallic compound.
Warranty information	<p>Please read carefully</p> <p>The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KCC's products are safe, effective, and fully satisfactory for the intended end use.</p> <p>KCC's sole warranty is that the product will meet the KCC sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to replacement of any product shown to be other than as warranted.</p> <p>KCC specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KCC provides you with a specific, duly signed endorsement of fitness for use, KCC disclaims liability for any incidental or consequential damages.</p> <p>Suggestions of use shall not be taken as inducements to infringe any patent.</p>
1'st issue	2007-01-08
Revision	2011-05-25

※ Please refer to MSDS if you want to know more specific usage or caution.
for further information, please see our website, www.kccworld.co.kr

