



Product description	SL7915 is a two-component liquid silicone rubber for General purpose. (Mixing ratio SL7915A : SL7915B = 100 : 100)
Applications	For general purpose
Key performance properties	High temperature vulcanizing and addition curing LSR

Typical Property Data

Benefits	No by-products because of addition curing LSR. Good flow-ability
----------	---

Typical properties	Property		Test method	Unit	Press 1st cure
	Before curing	Appearance	PTA	ASTM E 1767	-
PTB			Translucent		
Viscosity		PTA	ASTM D 4287	Pa·s	5
		PTB		mPa·s	5
Mixing ratio (by weight)				1 : 1	
General properties	Appearance		ASTM E 1767	-	Translucent
	Curing time(110°C, T60)		ASTM D 5289	sec	25
	Specific gravity (at 23°C)		ASTM D 792	-	1.05
	Hardness		ASTM D 2240	Shore A	15
	Tensile Strength		DIN 53504	MPa	3
	Elongation		DIN 53504	%	850
	Tear Strength		ASTM D 624	N/mm	8

1) Shear Rate 10 s⁻¹

2) Sheet curing conditions : press cure at 170°C/10 min

3) ASTM D624-B

Caution) Typical property data values should not be used as specifications

Composition	- Silicone polymer - Silica
How to use	For making a suitable product, Mix components SL7915A and SL7915B in the ratio 100 : 100
Features	- High temperature vulcanizing and addition curing LSR

Storage and packaging

Shelf life and storage	Use it within 12 months from the day of manufacture. Store in a cool dry place out of direct sunlight. Keep out of the reach of the children.
Packaging	SL7915A : 20 kg Straight PE Pail SL7915B : 20 kg Straight PE Pail

Remarks

Handling	Wear eye protection and protective glove when handling this product.
Precautions	May cause a curing difficulty with amine, sulfur, organicphosphate compound, and organometalic

	compound.
Warranty information	<p>Please read carefully</p> <p>The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that KCC's products are safe, effective, and fully satisfactory for the intended end use.</p> <p>KCC's sole warranty is that the product will meet the KCC sales specifications in effect at the time of shipment. Your exclusive remedy for breach of such warranty is limited to replacement of any product shown to be other than as warranted.</p> <p>KCC specifically disclaims any other express or implied warranty of fitness for a particular purpose or merchantability. Unless KCC provides you with a specific, duly signed endorsement of fitness for use, KCC disclaims liability for any incidental or consequential damages.</p> <p>Suggestions of use shall not be taken as inducements to infringe any patent.</p>
1'st issue	2015-09-08
Revision	

※ Please refer to MSDS if you want to know more specific usage or caution.
for further information, please see our website, www.kccworld.co.kr

